

Table 17.1. Summary of the quarry database with mean variable values for the 13 white marbles used to provenance the Villa A artifacts.

No.	Marble group, number of samples	MGS mm	$\delta^{18}\text{O}$ ‰	$\delta^{13}\text{C}$ ‰	Intensity EPR %	Width EPR %	Color %
1	Carrara (Luna), 112	0.80	-1.89	2.11	68.5	63.4	82.7
2	Hymettos, 41	0.69	-2.17	2.20	14.2	46.0	71.4
3	Penteli (Mt. Pentelikon), 154	0.96	-7.00	2.63	226.3	58.2	89.8
4a	Paros I, Lychnites, 41	1.70	-3.25	4.27	8.6	48.6	84.7
4b	Paros II, Chorodaki, 62	2.07	-1.11	1.79	19.5	47.9	83.9
4c	Paro II, Marathi	2.11	-2.59	1.97	9.8	52.0	79.7
5	Afyon (Dokimeion)	0.86	-4.32	1.80	242.5	53.9	75.7
6	Miletos	1.49	-2.56	2.05	17.7	53.2	81.5
7	Aphrodisias, 103	2.12	-3.53	1.34	43.4	53.7	81.6
8a	Ephesos 1, 88	1.74	-4.42	3.81	60.0	56.4	74.9
8b	Ephesos 2, 38	1.71	-3.14	0.35	41.8	45.5	76.1
9a	Prokonnesos 1, 348	1.72	-2.26	2.66	5.0	58.5	77.6
9b	Prokonnesos 2, 14	1.65	-6.72	2.62	4.3	58.5	76.9

